



Features

Applications

- **Compatibility:**
realNA — most accurate fiber core NA for minimal splice loss
Glass cladding diameter is designed to “fit-in” octagonal active fibers
Fiber Bragg Gratings can be written into all large mode area passive fibers
- **Reliability:**
Double cladding fiber coating proven to operate up to 150°C and in extreme humidity

- Fiber-based components for fiber lasers (e.g. pump combiners; FBGs)
- Pigtails for fiber lasers and amplifiers
- All-fiber subassemblies

Typical Fiber Specifications

LIEKKI® Fiber	Passive-20/250DC, 0.07NA	Passive-20/250DC
Optical	Units	
Core Numerical Aperture	0.070 ± 0.005	0.080 ± 0.005
Cladding Numerical Aperture, ≥	0.48	
Core Background Loss at 1200 nm, ≤ dB/km	5.0	
Geometrical and mechanical		
Core Diameter	μm	20.0 ± 1.5
Core Concentricity Error, ≤	μm	1.0
Cladding Diameter	μm	250 ± 5
Cladding Geometry	Round	
Coating Diameter	350 ± 15	
Coating Material	Dual coated low index acrylate	
Proof Test, ≥	kpsi	100

nLIGHT continually improves its products to provide outstanding quality and reliability. The information contained herein is subject to change without notice. nLIGHT, Inc. shall not be liable for technical or editorial errors or omissions contained herein. Warranties are set forth in express warranty statements accompanying products. Nothing herein should be constituting an additional warranty. For details, please contact your nLIGHT sales representative.